



Theoretic Powder Coating Coverage Chart (Metric)

TIGER Drylac® U.S.A., Inc.

1-800-243-8148

WEST COAST (HQ)

1261 East Belmont St.
Ontario, CA 91761
phone 909 930 9100
fax 909 930 9111
customerservicewest@tigerdrylac.com
www.tigerdrylac.com

MIDWEST

3855 Swenson Ave.
St. Charles, IL 60174
phone 630 513 9999
fax 630 513 9998
customerservicemw@tigerdrylac.com

EAST COAST

1100 Commons Blvd.
Reading, PA 19605
phone 610 926 8148
fax 610 926 8149
customerserviceeast@tigerdrylac.com

SOUTHEAST

3400 Town Point Drive NW Ste. 140
Kennesaw, GA 30144
phone 770 218 2490
fax 770 218 2495
customerservicese@tigerdrylac.com

SOUTH

339 Exchange Drive
Arlington, TX 76011
phone 817 277 7995
fax 817 277 1931
customerservicesouth@tigerdrylac.com

THEORETICAL YIELD OF TIGER DRYLAC® POWDER COATINGS

in [sq.m.] of surface to be coated per [kg] of powder.

Specific Gravity [g/cm ³]	FILM THICKNESS									
	1 mil 25 µm	2 mil 50 µm	3 mils 75 µm	4 mils 100 µm	5 mils 125 µm	6 mils 150 µm	7 mils 175 µm	8 mils 200µm	9 mils 225 µm	10 mils 250 µm
1.0	40.0	20.0	13.3	10.0	8.0	6.7	5.7	5.0	4.4	4.0
1.1	36.4	18.2	12.1	9.1	7.3	6.1	5.2	4.5	4.0	3.6
1.2	33.3	16.7	11.1	8.3	6.7	5.6	4.8	4.2	3.7	3.3
1.3	30.8	15.4	10.3	7.7	6.2	5.1	4.4	3.8	3.4	3.1
1.4	28.6	14.3	9.5	7.1	5.7	4.8	4.1	3.6	3.2	2.9
1.5	26.7	13.3	8.9	6.7	5.3	4.4	3.8	3.3	3.0	2.7
1.6	25.0	12.5	8.3	6.3	5.0	4.2	3.6	3.1	2.8	2.5
1.7	23.5	11.8	7.8	5.9	4.7	3.9	3.4	2.9	2.6	2.4
1.8	22.2	11.1	7.4	5.6	4.4	3.7	3.2	2.8	2.5	2.2
1.9	21.1	10.5	7.0	5.3	4.2	3.5	3.0	2.6	2.3	2.1
2.0	20.0	10.0	6.7	5.0	4.0	3.3	2.9	2.5	2.2	2.0

Values in [sq.m. / kg]

Theoretical yield values not found in the above table may be calculated using the following formula:

$$\frac{1.000}{(\text{Specific Gravity}) \times (\text{Film Thickness})} = \text{Theoretical Yield in [sq.m. / kg]}$$

These are some of the variables that may account for a difference between theoretical and actual yield:

- Powder loss in the process of cleaning the booth, hoses, application equipment and fluid mixer
- Powder loss through recycling in cyclone equipment
- Un-recycled overspray
- Variation in film thickness of coated parts
- Variable surface roughness (e.g. sandblasted parts)

As a part of our product information program our product data sheets are periodically updated. Therefore, please check our webpage for the latest edition. Our verbal and written recommendations for the use of our products are based upon experience and in accordance with present technological standards. These are given in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of our products for the intended application. This product data sheet substitutes any and all previous product data sheet and notes for customers published on this subject matter.