

SERIES 16 - military powder coating

POLYESTER WEATHER RESISTANT POWDER COATING FOR MILITARY APPLICATIONS

Typical applications

- water tanks
- camouflage
- support and communication equipment
- general military applications

Product details

- Standard packaging** in original 44 lb (20 kg) box and 5 lb (2.5 kg) minipack
- Specific gravity (ASTM D792)** approximately 1.60 g/cm³ depending on pigmentation
- Theoretical coverage** at 2.5 mils (60 µm) film thickness: **51.5 ft²/lb (11.1 m²/kg)**. Refer also to the latest edition of "Theoretic Powder Coating Coverage Chart" version 00-1001 (imperial) version 00-1000 (metric)
- Storage stability** 3 months at no more than 77 °F (25 °C) avoid direct and extended exposure to heat

Features

- good weather resistance
- good storage stability

Pretreatment

Refer to TT-C-490 for ferrous substrates and TT-C-490/MIL-C-5541F for non-ferrous substrates

Processing

Corona and Tribostatic*

* For Tribostatic powder coatings, confirm before ordering. Suitability of metallic effects for Tribostatic processing must be verified prior to actual application. Please refer to the latest edition of the relevant application guidelines for metallic effect powder coatings

Since not all powder coatings are suitable for recycling/reclaim, please verify before ordering

Finish

finish	gloss
smooth <i>flat matte</i>	>3-8*
fine texture	visual


* Gloss level according to ASTM 523 at 60° angle (doesn't apply to metallic effect powder coatings). The measured gloss level of effect powder coatings can diverge from the details given in this Product Data Sheet. The creation of tolerance samples is recommended

Available as stock-product in a selection of colors and finishes (see following table and color charts)

product description	product ID
Olive Drab Fed Std 34079	316/50012
Green Fed Std 34094	316/50025
Green Fed Std 34094	16/50016
Desert Tan Fed Std 33446	16/15022
British Brown Fed Std 30145	16/15014
Black Camo Fed Std 37030	16/80061

Cure parameters

(substrate temperature versus curing time)



Cure parameters must be closely observed since mechanical properties will develop before full cross-linking

Test results

Checked under laboratory conditions on iron phosphated steel test panels Bonderite B-1000 or equivalent. Cure conditions are according to the cure curves. Actual product performance may vary due to product-specific properties such as gloss, color, effect and finish as well as application-related and environmental influences. When used as a two-coat system, the increase in film thickness will result in a decrease of mechanical properties.

test method	test	Series 16 smooth flat matte
ISO 2360	recommended film thickness	2.5-3.5 mils (60-80 µm)
ASTM D3359 method B	cross cut tape test 1mm cutting distance	5B
ASTM D522	mandrel bending test cracking of coating	≤1/2 inch (≤12 mm)
ASTM D2794	ball impact test cracking of coating	80in/lb no appearance of cracks down to the substrate
ASTM D3363	pencil hardness	2H minimum
ASTM D2247	determination of resistance to humidity 500 hours	maximum undercutting 1/32 inch (1 mm), no blistering
ASTM B117	salt spray resistance 500 hours	maximum undercutting 1/32 inch (1 mm), no blistering
JP8 hydrocarbon fluid	hydrocarbon resistance	no change
ASTM G 154	accelerated weathering 1,000 hours QUV-A	minimal change of color and gloss
Spot test for 30 minutes	DS2P resistance	no major color and gloss change
1 hour resistance to 10% acetic acid	acid resistance	no blistering

Cleaning recommendations: refer to the latest edition of TIGER "Cleaning Recommendations" information sheet, Version 00-1005

Please note

Top coating with a clear exterior grade powder coating over an interior grade powder coating does not result into a weather resistant coating system.

Post-bending properties of any part must be verified prior to application. Minor cracks in the coated surface may lead to corrosion.

Joint sealants and any other auxiliary products, such as glazing aids, gliding waxes, drilling and cutting lubricants, which come in contact with the coated surface, must be pH-neutral and free of substances that may damage the finish. Therefore, a suitability test at the applicator's end, prior to coating, is highly recommended.

In general, colors in the red, orange and yellow range may require an increased film thickness to achieve full hiding.

Please read and understand the Safety Data Sheet (SDS) before use.

Chemical resistance

The required chemical resistance of a powder coating depends, among other things, on its formulation. Chemical resistance requirements must be considered according to processing conditions and final use of the finished product. This is best established during the product specification process. Agreement between all parties involved must be reached about the requirements for such chemical resistance as well as the test method, which may be performed in accordance with PCI test method #8 "Solvent Cure Test". Furthermore, the test duration and concentration of the test media need to be agreed upon.

Disclaimer

TIGER's verbal and written recommendations for the use of its products are based upon experience and in accordance with current technological standards. These are provided in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of TIGER products for the intended application. TIGER warrants that its products are free of flaws and defects to the extent stipulated in the Terms of Delivery and Payment.

As part of TIGER product information program, each Product Data Sheet is updated periodically. The latest version shall prevail. It is recommended to always check for the latest editions on TIGER's website download area www.tiger-coatings.com to make sure you have the most current version of this Product Data Sheet. The information on TIGER's Product Data Sheets are subject to change without notification.

This Product Data Sheet supersedes and replaces all previous Product Data Sheet versions and notes to customers published in relation to this product and is only intended to provide a general overview on the product.

Latest versions of Technical Information Sheets and Terms of Delivery and Payment are downloadable from www.tiger-coatings.com and form an integral part of this Product Data Sheet.